



# STRUCTURE SPRAY (TYPE 3)

...for netball courts

Polymeric Structure Spray (Type 3) consists of an SBR shockpad with a 2-3mm spray coating of granulated EPDM rubber and a non-slip coating.


The non-slip coating gives the surface high skid resistant properties which are needed for courts used for netball only.

The spray is available in a variety of colours, including red, green or blue.

## Key Specifications

- 5 year warranty\*\*
- IAAF tested
- Anti-slip properties (TRRL 75)
- Shock absorption to reduce impact force when running
- Porous
- Designed to meet Sport England MUGA 3 specifications

## RECOMMENDED BUILD UP TO CREATE A PERMEABLE SURFACE:



- Line markings
- Non slip coating
- 2-3mm of 0.5-1.5mm EPDM rubber granules
- 9-10mm SBR rubber shockpad
- 25mm AC6 open textured surface course macadam
- 50mm AC20/14 open textured macadam
- Min 100-300mm MOT type 1 dependent on ground conditions
- Geotextile membrane
- Edge options: Concrete, Aluminium, Rubber

“ We have been using DCM Surfaces for many years now and always find the team to be very knowledgeable, professional and willing to go the extra mile to ensure the job is completed to a very high standard within the set time.

Managing Director, HAGS

”

\*\*Terms and Conditions apply.

T. +44 (0)1772 440340 E info@dcmsurfaces.com

[WWW.DCMSURFACES.COM](http://WWW.DCMSURFACES.COM)

# STRUCTURE SPRAY (TYPE 3)

## Base

The base must be dry and of sound construction.

SURFACE DEPTH	CONCRETE	MACADAM	WETPOUR	FLAGS	SOIL / GRASS	MOT TYPE 1
9-10mm SBR	✓	✓	✗	✗	✗	✗

## SBR Shockpad Technical Data

TECHNICAL DATA	VALUE
Material	SBR rubber. 8% min binder content
Curing Period	4 - 24 hours, dependent on area size







## Structure Spray Technical Data

TECHNICAL DATA	VALUE
Material: Top Layer	0.5 - 1.5mm EPDM coloured granules 18% min binder content
Material: Bottom Layer	2-6mm recycled rubber granules 8% min binder content
Curing Period	12 hours
Certifications	Principle materials standard: BS EN 14877  Slip resistance: BS EN 13036-4 (TRR $\geq$ 75 within 5C-30C)  Shock absorption: BS EN 14808  Tensile strength: BS EN 12330  Surface regularity: BS EN 13036-7  Water permeability: BS EN 12616



## Structure Spray Colour Chart

STANDARD			PREMIUM	
				
Red	Light Green	Dark Green	Light Blue	Dark Blue

\* Additional colours available on request